



THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

Epoxy Coated Nomex® 410 Aramid Paper

Item:	Epoxy Coated Nomex® 410 Aramid Paper					
Description:	Epoxy Coated Nomex® is an Aramid fiber paper (Nomex® 410) that is coated on one or both sides with a B-staged high-temperature epoxy resin. The Gund Company can custom fabricate this material to the exact specifications and drawings of our customers.					
Processing Directions:	Recommended parameters are 350°F at 90 psi for five seconds to bond and 15 minutes to initiate cure. However, each user should determine the parameters that best suit the equipment, with running speeds adjusted to permit heat transfer through the Aramid paper to the second coated side. This is a heat sensitive material and should be stored in a cool place. The manufacturer recommends a six-month shelf life.					
Availability:	One-Sided Coat:	Base Thickness	Resin Thickness	Total Thickness	Tolerance	
		0.003" (0.08 mm)		0.0006" (0.015 mm)		0.0036" (0.09 mm)
		0.005" (0.13 mm)				0.0056" (0.14 mm)
		0.007" (0.18 mm)				0.0076" (0.19 mm)
		0.01" (0.25 mm)				0.0106" (0.27 mm)
	0.015" (0.4 mm)	0.0156" (0.40 mm)				
	Two-Sided Coat:	0.003" (0.08 mm)	0.0012" (0.03 mm)	0.0042" (0.11 mm)	± 0.0003" (0.008 mm)	
		0.005" (0.13 mm)		0.0062" (0.16 mm)		
		0.007" (0.18 mm)		0.0082" (0.20 mm)		
		0.01" (0.25 mm)		0.0112" (0.28 mm)		
		0.012" (0.3 mm)		0.0132" (0.34 mm)		
		0.015" (0.4 mm)		0.0162" (0.41 mm)		

Key Characteristics	Test Method	Units - English (SI)	Typical Values	
			0.006"	0.012"
Yield	--	lbs/yd ²	0.21	0.046
Dielectric Strength	ASTM D-149	Volts	3,650	8,800
Tensile Strength, MD	ASTM D-828	lbs./in.	83	180
Dielectric Constant, 60 Hz	ASTM D-150	--	3.0	3.1
Dissipation Factor, 60 Hz	ASTM D-150	--	0.01	0.01
Volume Resistivity	ASTM D-257-66	Ohm - cm	10 ¹⁷	10 ¹⁷
Surface Resistivity	ASTM D-257-66	Ohm - cm	10 ¹⁴	10 ¹²
Operating Temperature	--	°C	-40	180

AS9100C Certified | ISO/AS9100 Certified QMS | RoHS Compliant | ITAR Compliant

Data supplied above are typical values and are not to be considered specification values. All of the information, suggestions and recommendations pertaining to the properties and uses of the products herein are based upon tests and data believed to be accurate; however, the final determination regarding suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty, expressed or implied, including, without limitation warranty of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.